

Product: igutek P360

General Properties:

density:	1.24 g/cm ³
colour:	light beige
saturation with moisture absorption at 23°C / 50% r. h.:	0.5 weight %
saturation with water:	2.1 weight %

Mechanical Properties:

flexural modulus:	1300 MPa
flexural strength:	50 MPa

Thermal Properties:

highest long term service temperature ¹⁾ :	110°C
highest short term service temperature ^{1), 2)} :	130°C
lowest service temperature:	-30°C

Electrical Properties:

surface resistivity:	>10 ¹² Ω
----------------------	---------------------

¹⁾ relaxation possible

²⁾ without additional load; no movement

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties.